



PRO-SET®

Technical Data

LAM-135 LAM-239

LAMINATING EPOXY

COMBINED FEATURES

Medium viscosity for good wet out of all synthetic composite fabrics and core materials.

Extended open time hardener provides 8 to 9 hours of working time at 85°F (29°C). A typical laminate will be gelled in 12 to 14 hours at 85°F (29°C).

Optimized for hand wet out and machine impregnation in contact molding, vacuum bagging and Light RTM applications.

Elevated temperature cure is required; thermal and mechanical properties suitable for composite components and high-temperature tooling and molds.

T_g as high as 215°F (102°C) with proper post cure providing excellent temperature stability and great part cosmetics.

Cost effective, high performance epoxy formulation for synthetic composite manufacturing.

The New Standard

EPOXIES for Laminating Infusion Tooling Assembly

Gougeon Brothers, Inc.
P.O. Box 908
Bay City, MI 48707
prosetepoxy.com
888-377-6738

ISO9001:2015 Certified

Rev 4 / Dec 2021

©2021 Gougeon Brothers, Inc.

HANDLING PROPERTIES

Property	Standard	Units	72°F (22°C)	77°F (25°C)	85°F (29°C)
150g Pot Life	ASTM D2471	minutes	223-272	187-228	142-194
500g Pot Life	ASTM D2471	minutes	162-198	123-151	94-116
Viscosity Mixed	ASTM D2196	cP	1976	1544	1085
Viscosity (resin)	ASTM D2196	cP	6,890		
Viscosity (hardener)	ASTM D2196	cP	116		


MIX RATIO

Method	Resin:Hardener	Resin:Hardener
Weight	3.5:1	100:27.9
Weight Range	4.28:1–3.08:1	100:23.4–100:32.5
Volume	3.00:1	100:33.3
Volume Range	3.59:1–2.58:1	100:27.9–100:38.8

DENSITY

State	Units	72°F (22°C)
Cured	lb/gal (g/cc)	9.68 (1.16)
Resin	lb/gal (g/cc)	9.71 (1.16)
Hardener	lb/gal (g/cc)	8.14 (0.98)

VISCOSITY VS TEMPERATURE



Test specimens were neat epoxy (without fiber reinforcement).
Typical values, not to be construed as specification.



LAM-135~LAM-239

LAMINATING EPOXY

MECHANICAL PROPERTIES

Property	Standard	Units	RT Gelation + 140°F (60°C) x 8 hrs	RT Gelation + 140°F (60°C) x 16 hrs	RT Gelation + 180°F (82°C) x 8 hrs
Hardness	ASTM D2240	Type D	86	91	86
Compression Yield	ASTM D695	psi (MPa)	14,100 (97)	14,100 (97)	14,100 (97)
Tensile Strength	ASTM D638	psi (MPa)	10,200 (70)	10,200 (70)	10,300 (71)
Tensile Modulus	ASTM D638	psi (GPa)	4.83E+05 (3.33)	4.58E+05 (3.16)	4.05E+05 (2.79)
Tensile Elongation	ASTM D638	%	4.8	6.2	6.3
Flexural Strength	ASTM D790	psi (MPa)	17,700 (122)	17,700 (122)	17,700 (122)
Flexural Modulus	ASTM D790	psi (GPa)	4.84E+05 (3.34)	4.84E+05 (3.34)	4.21E+05 (2.9)

THERMAL PROPERTIES

Property	Standard	Units	RT Gelation + 140°F (60°C) x 8 hrs	RT Gelation + 140°F (60°C) x 16 hrs	RT Gelation + 180°F (82°C) x 8 hrs
Tg DMA Peak Tan Delta	ASTM E1640 ¹	°F (°C)	210 (99)	219 (104)	241 (116)
Tg DMA Onset Storage Modulus	ASTM E1640 ¹	°F (°C)	181 (83)	188 (87)	215 (102)
Tg DSC Onset– 1st Heat	ASTM E1356	°F (°C)	167 (75)	169 (76)	215 (102)
Heat Deflection Temperature	ASTM D648	°F (°C)	162 (72)	174 (79)	208 (98)
Tg DSC Ultimate	ASTM E1356	°F (°C)		221 (105) ²	

¹ 1 Hz, 3°C per minute.

² Additional post cure may be required; contact Technical Department for details.

³ Store PRO-SET® Epoxy resins and hardeners at room temperature in sealed containers until shortly before use. As with many high-performance epoxy resins, repeated exposure to low temperatures during storage may cause the resin to crystallize. If this occurs, warm the resin to 125° F and stir to dissolve crystals. Hardeners may form carbamation when exposed to CO₂ and moisture in the atmosphere for extended periods of time. Prevent carbamation by protecting hardeners from exposure until immediately prior to processing.



Shelf Life



QC Tinting Available

Rev 4 / Dec 2021